AMENDMENTS TO THE CLAIMS

This listing of claims replaces all prior versions of claims in the application.

Claim 1 (currently amended): A sintered nickel electrode for an alkaline storage battery

in which an intermediate layer of an active material mainly containing nickel hydroxide is

applied to a porous sintered nickel substrate, characterized in that a coating layer containing

consisting of at least one hydroxide of an element selected from the group consisting of strontium

Sr, scandium Sc, yttrium Y, the lanthanoid elements, and bismuth Bi is formed on a surface of

the intermediate layer opposite the porous sintered nickel substrate.

Claim 2 (previously presented): A sintered nickel electrode for an alkaline storage battery

in which an intermediate layer of an active material mainly containing nickel hydroxide is

applied to a porous sintered nickel substrate, characterized in that a coating layer containing

cobalt together with at least one hydroxide of an element selected from the group consisting of

calcium Ca, strontium Sr, scandium Sc, yttrium Y, the lanthanoid elements, and bismuth Bi is

formed on a surface of the intermediate layer opposite the porous sintered nickel substrate.

Claim 3 (previously presented): The sintered nickel electrode for an alkaline storage

battery according to claim 2, characterized in that said coating layer containing cobalt is heat-

treated in the presence of alkali and oxygen.

Page 2

Amendment under 37 C.F.R. §1.116

Serial No. 09/622,615

Attorney Docket No. 000774

Claim 4 (previously presented): The sintered nickel electrode for an alkaline storage

battery according to claim 1, characterized in that said lanthanoid is at least one element selected

from the group consisting of lanthanum La, cerium Ce, praseodymium Pr, neodymium Nd,

europium Eu, and ytterbium Yb.

Claim 5 (previously presented): The sintered nicked electrode for an alkaline storage

battery according to claim 1, characterized in that an amount of said hydroxide in the coating

layer is in the range of 0.5 to 5 wt% based on the total amount of all the applied materials which

includes the active material mainly containing nickel hydroxide.

Claims 6-10 (canceled)

Claim 11 (previously presented): An alkaline storage battery characterized in that the

sintered nickel electrode for an alkaline storage battery according to claim 1 is used as its positive

electrode.

Claims 12-25 (canceled)

Claim 26 (previously presented): An alkaline storage battery characterized in that the

sintered nickel electrode for an alkaline storage battery according to claim 2 is used as its positive

electrode.

Page 3